



# NOTES:

STEEL VENT PIPE UNLESS OTHERWISE SPECIFIED SHALL BE SCHEDULE 40, FIVE INCH (5") DIAMETER, GRADE "B" WITH A MINIMUM YIELD STRENGTH OF 35,000 P.S.I.

THE STEEL PIPE SHALL HAVE AN INSIDE COAL TAR LINING 3/32 INCH MINIMUM THICKNESS INACCORDANCE WITH AWWA C-203 OR A COAL TAR EPOXY LINING CONFORMING TO THAT REQUIRED FOR AERIAL CREEK CROSSING PIPE.

OUTSIDE SURFACE OF PIPE SHALL BE SAND OR GRIT BLASTED TO COMMERCIAL STANDARD AND HAVE ONE (1) COAT OF ZINC CHROMATE PRIMER APPLIED IN ACCORDANCE WITH FEDERAL SPECIFICATION TT-86A.

PIPE SHALL BE FURNISHED WITH TWO (2) EVENLY APPLIED COATS OF RUST INHIBITING ENAMEL PAINT.

#	REVISED	DATE: 7/1/04	STANDARD DETAIL	WATER RESOURCES DEPARTMENT CITY OF MONROE, NC	
	1/26/17	SCALE: NONE			
		DRAWN BY: EZ	VENTED MANHOLE DETAIL	FILE NO. 12.08.00	DIV. NO. 12
		CHECKED BY: DSW			
		APPROVED BY: DSW			